

Grade B



Canter Quarry



Sand



Saddle



Safari



Chestnut



Sumac



Iron



Earth



Baltic



Alfalfa



Ink



Sable



Onyx

Grade C



Beeline Valley



Canvas



Sisal



Spice



Geyser



Jetty



Eclipse

Grade D



Row Stone



Cream



Breeze



Cloud



Organic



Magic



Shale



Basket



Rain



Sage



Fjord



Coffee



Nightfall

Grade F



Silica Alloy



Lotus



Lemon



Appletini



Brownstone



Quartz



Breakwater



Ginger



Firelight



Coppercrest



Gallant



Manor



Nero


54" - Pattern	Fiber Content & Backing	Finish	Abrasion (D.R.)	Light-fastness	Approx. Repeats	Cleaning Code	Grade
BEELINE ▲▲▲●●★*	100% Polyurethane / PVC Free Polyester Backing	Anti-microbial, Anti-bacterial	500,000	200 Hrs. Class 4.5		W Bleach Cleanable (4:1)	C
CANTER ▲▲▲●●★*	100% Polyurethane / PVC Free Polyester Backing	Anti-microbial, Anti-bacterial	240,000	200 Hrs. Class 4.5		W Bleach Cleanable (4:1)	B
ROW ▲▲▲●●★*	100% Polyurethane / PVC Free Polyester Backing	Anti-microbial, Anti-bacterial	500,000	200 Hrs. Class 4.5	Shown Railroaded	W Bleach Cleanable (4:1)	D
SILICA ▲▲▲●●★*	100% Silicone Polyester Backing	n/a	365,000	200 Hrs. Class 4.5		WS Bleach Cleanable (4:1)	F

*ACT® Registered Certification Marks

EXPLANATION OF ACT ICONS FOR UPHOLSTERY

FIRE RETARDANCY

Flammability testing determined as fabric's resistance to burning.

 **PASSES**
California 117 2013

COLORFASTNESS TO WET & DRY CROCKING

Colorfastness to wet & dry crocking refers to the rubbing off of color from the fabric onto clothing, hands or other materials and can occur under wet or dry conditions.

 **PASSES**
AATCC 8-1974 Dry Crocking, Class 4 minimum; Wet Crocking, Class 3 minimum

COLORFASTNESS TO LIGHT

Colorfastness to light is the degree to which fabric will retain its color when exposed to light.

 **PASSES**
AATCC 16A-1974 or AATCC 16E-1976; Class 4 minimum at 40 hours
NOTE: Class 4 minimum at 60 hours is recommended for direct sunlight exposure situations

PHYSICAL PROPERTIES

3 physical property tests include: brush pill test to determine a fabric's pilling. Breaking/tensile strength is the ability of a fabric to withstand tension without breaking or tearing. Seam slippage is the pulling apart of fabrics at the seams.

 **PASSES**
Brush Pill ASTM D3511, 3-4 minimum
Breaking Strength ASTM D3597-D1682-64 (1975) 50 lbs. minimum in warp & weft
Seam Slippage ASTM D3597-D434-75 25 lbs. minimum in warp & weft

For memo samples please contact:

MOMENTUM
TEXTILES



Toll Free 800-366-6839
memosamples.com



GREENGUARD Certified. CA Section 01350 compliant.
Eligible for CHPS Low-Emitting Material Credits.

ABRASION

Abrasion is the ability of a fabric to withstand damage from wear and rubbing. There is a general contract specification as well as a heavy duty specification.

PASSES
 **General Contract** ASTM 3597 modified (#10 cotton duck); 15,000 double rubs Wyzenbeek Method
 **Heavy Duty** ASTM 3597 modified (#10 cotton duck); 30,000 double rubs Wyzenbeek Method or ASTM D4966 (with 21 oz. weight); 40,000 rubs Martindale Method

CLEANING CODE DEFINITIONS

W: Water-based foam or cleaner.

WS: Water-based cleaning agents or foam.

9to5
seating

9 to 5 Seating
3211 Jack Northrop Ave.
Hawthorne, CA 90250
Tel: 888.925.SEAT --> 888.925.7328
Fax: 866.925.SEAT --> 866.925.7328